

# Jollyboard LIMITED

25 Km. Stone, Miraj - Pandharpur Road,  
Deshing - 416 410  
Tal. Kawathe Mahankal, Dist. SANGLI.  
Telephone No.: 9921001239  
Email: sangli@jollyboard.com  
CIN : U20200MH1956PLC009899

## Test Report


[ 10MM 5%Bitumen Black Soft Board ]

Bispee Bangalore

| Sr. No. | PARAMETERS          | Board sample | Sample No. 1 | Sample No. 2 | sample No3 |
|---------|---------------------|--------------|--------------|--------------|------------|
| 01      | Thickness in mm     | 10.5mm       | 10.3         | 10.5         | 10.1       |
| 02      | MOR ( Kg/Cm2 )      | Min 20       | 20.2         | 20.8         | 20.5       |
| 03      | Density ( Kg/m3)    | Min 280      | 285          | 287          | 280        |
| 04      | Colour & Appearance | Black        | black        | black        | black      |
| 05      | Bitumen %           | Min 5%       | 5.04         | 5.11         | 5.15       |

Regards,

JollyBoard Ltd. Sangli

  
Chemist



Registered Office:  
501, Rewa Chambers,  
31 Sir V. Thackersey Marg,  
Mumbai 400 020, INDIA  
Tel : (022) 22078531-34

# Jollyboard LIMITED

25 Km. Stone, Miraj - Pandharpur Road,  
Deshing - 416 410  
Tal. Kawathe Mahankal, Dist. SANGLI.  
Telephone No.: 9921001239  
Email: sangli@jollyboard.com  
CIN : U20200MH1956PLC009899

## TEST REPORT

### [ 18 MM 5%BITUMEN SOFT BOARD]


Bispee Bangalore

| Dt.sr.<br>No. | PARAMETERS                    | Limits       | Sample No. 1 | Sample No. 2 | Sample No. 3 |
|---------------|-------------------------------|--------------|--------------|--------------|--------------|
|               |                               |              |              |              |              |
| 01            | Thickness in MM               | 18 to 18.5mm | 18.1         | 18.4         | 18.5         |
| 02            | MOR ( Kg/cm <sup>2</sup> )    | Min 20       | 20.8         | 20.2         | 209          |
| 03            | Density ( Kg/M <sup>3</sup> ) | Min 280      | 298          | 295          | 300          |
| 04            | Colour & Appearance           | Black        | Black        | Black        | Black        |
| 05            | Bitumen %                     | Min 5%       | 5.14         | 5.04         | 5.10         |

Regards,

Jollyboard Limited. Sangli

  
Chemist



Registered Office:  
501, Rewa Chambers,  
31 Sir V. Thackersey Marg,  
Mumbai 400 020, INDIA  
Tel : (022) 22078531-34

# Jollyboard LIMITED

25 Km. Stone, Miraj - Pandharpur Road,  
Deshing - 416 410  
Tal. Kawathe Mahankal, Dist. SANGLI.  
Telephone No. : 9921001239  
Email: sangli@jollyboard.com  
CIN : U20200MH1956PLC009899

## TEST REPORT

[ 22 MM 5%BITUMEN SOFT BOARD]

Bispee Bangalore

| Dt.sr.<br>No. | PARAMETERS          | Limits          | Sample No. 1 | Sample No. 2 | Sample No. 3 |
|---------------|---------------------|-----------------|--------------|--------------|--------------|
| 01            | Thickness in MM     | 22 to<br>22.5mm | 22.1         | 22.4         | 22.5         |
| 02            | MOR ( Kg/cm2 )      | Min 16          | 16.8         | 16.2         | 16.9         |
| 03            | Density ( Kg/M3)    | Min 280         | 298          | 295          | 300          |
| 04            | Colour & Appearance | Black           | Black        | Black        | Black        |
| 05            | Bitumen %           | Min 5%          | 5.14         | 5.04         | 5.10         |

Regards,

Jollyboard Limited. Sangli

  
Chemist



Registered Office:  
501, Rewa Chambers,  
31 Sir V. Thackersey Marg,  
Mumbai 400 020, INDIA  
Tel : (022) 22078531-34

# Jollyboard LIMITED

25 Km. Stone, Miraj - Pandharpur Road,  
Deshing - 416 410  
Tal. Kawathe Mahankal, Dist. SANGLI.  
Telephone No : 9921001239  
Email: sangli@jollyboard.com  
CIN : U20200MH1956PLC009899

## Test Report


[ 10MM 5%Bitumen Black Soft Board ]


Taaraadin Engineering Ernakulam.

| Sr. No. | PARAMETERS          | Board sample | Sample No. 1 | Sample No. 2 | sample No3 |
|---------|---------------------|--------------|--------------|--------------|------------|
| 01      | Thickness in mm     | 10.5mm       | 10.3         | 10.5         | 10.1       |
| 02      | MOR ( Kg/Cm2 )      | Min 20       | 20.2         | 20.8         | 20.5       |
| 03      | Density ( Kg/m3)    | Min 280      | 285          | 287          | 280        |
| 04      | Colour & Appearance | Black        | black        | black        | black      |
| 05      | Bitumen %           | Min 5%       | 5.04         | 5.11         | 5.15       |

Regards,

JollyBoard Ltd. Sangli

  
Chemist



Registered Office:  
501, Rewa Chambers,  
31 Sir V. Thackersey Marg,  
Mumbai 400 020 INDIA  
Tel : (022) 22078531-34